

# MasterEmaco<sup>®</sup> P 130

Fast-setting epoxy primer for concrete surfaces

FORMERLY NITOPRIME<sup>®</sup> 30

## PACKAGING

3 GAL (11.4 L) KITS

– Part A: 2 gal (7.6 L)

– Part B: 1 gal (3.8 L)

## YIELD

150–200 ft<sup>2</sup> per gal (3.7–7.4 m<sup>2</sup>/L),  
depending on substrate texture  
and porosity

## STORAGE

Store and transport in unopened  
containers in a cool, clean, dry area.  
Keep from freezing.

## SHELF LIFE

2 years when properly stored

## VOC CONTENT

0 g/L less water and exempt solvents

## DESCRIPTION

MasterEmaco P 130 is a two-component low viscosity 100% solids fast-setting epoxy primer for concrete. It is used to consolidate concrete surfaces and enhance the adhesion of Master Builders Solutions epoxy coatings.

## PRODUCT HIGHLIGHTS

- Low viscosity ensures maximum penetration into concrete
- Excellent adhesion provides secure bonds to concrete
- Prepackaged kits for easy mixing and application
- Fast setting, ready for protective coatings in 3–4 hours
- Moisture insensitive product can be applied to either dry or damp surfaces
- 100% solids for no solvents, zero VOCs, and low odor

## APPLICATIONS

- Horizontal surfaces
- Interior
- Before applying MasterProtect<sup>®</sup> 170 CR and MasterProtect 100 CR
- For priming metal (repaired to near-white metal conditions according to SSPC-SP10)

## SUBSTRATES

- Concrete
- Masonry
- Metal

## HOW TO APPLY

### SURFACE PREPARATION

1. Concrete substrates must be fully cured (28 days), clean, and sound; they can be dry or damp but with no standing water.
2. Remove all grease, oil, chemical contamination, dust, laitance, and loose concrete by mechanical profiling to ICRI CSP 4 to provide a sound substrate.
3. Complete all necessary repairs prior to application and allow surface to reach loadbearing strength.

### MIXING

1. Precondition all components to 70° F (21° C) for 24 hours before using.
2. If the entire kit of MasterEmaco P 130 will not be used, smaller quantities can be mixed in the ratio of 2:1 (A:B) Mix ratios are critical; measure carefully.
3. Premix each of the components thoroughly, until homogeneous, using a Jiffy paddle attached to a low-speed (400–600 rpm) heavy-duty drill.
4. In a separate mixing vessel add Part A, then Part B. Stir until uniform in color without streaks, approximately 3 minutes. Scrape the sides of the containers, removing as much material as possible to ensure correct mixing ratios.

## Technical Data

### Composition

MasterEmaco P 130 is a two-component 100% solids epoxy.

### Typical Properties

PROPERTY	VALUE
<b>Solids, %</b> , by volume	100
<b>Mix Ratio</b> , by volume, A to B	2 to 1
<b>Viscosity</b> , mixed, cps, at 77° F (25° C)	800
<b>Pot life (100 g)</b> , min, 100g	
50° F (10° C)	30
70° F (21° C)	15
85° F (29° C)	5
<b>Cure times</b> , tack free, hrs	
50° F (10° C)	4–6
70° F (21° C)	2–4

Test results are averages obtained under laboratory conditions. Expect reasonable variations.

All application and performance values are typical for the material, but may vary with test methods, conditions, and configurations.

Unless otherwise noted, test samples were cured 7 days at 73° F (23° C) and 50 % relative humidity.

## APPLICATION

1. Brush, squeegee, or roll the mixed MasterEmaco P 130 onto the prepared concrete surface. Take care to avoid puddling in depressions.
2. If the primer is absorbed within 30 minutes, apply a second coat. If the primer becomes contaminated, it must be sanded and reapplied.
3. Apply MBT protective coatings after the primer is tack free—approximately 3–4 hours. Maximum recoat time is 48 hours.

## CLEAN UP

- Clean equipment immediately after use with xylene.
- Clean hands and skin immediately with soap and water, industrial hand cleaner, or denatured alcohol.
- Cured material must be removed mechanically.

## FOR BEST PERFORMANCE

- Minimum air, substrate, and material application temperature is 50° F (10° C). Lower temperatures will significantly slow curing time.
- Do not apply if temperature exceeds 90° F (32° C). Large quantities of mixed material and high ambient temperatures will reduce pot life significantly.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit [master-builders-solutions.basf.us](http://master-builders-solutions.basf.us) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and are not for supervising or providing quality control on the jobsite.

## HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.basf.us](http://www.master-builders-solutions.basf.us), e-mailing your request to [basfbcst@basf.com](mailto:basfbcst@basf.com) or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,  
call ChemTrec® 1(800)424-9300.**

## LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.