

MasterKure® CC 300 SB

Transparent, modified acrylic, solvent-based, high-gloss curing, sealing and dustproofing compound

FORMERLY KURE-N-SEAL™ 30

PACKAGING

MasterKure CC 300 SB:
5-gallon pails (18.9 L)
55-gallon drums (208 L)

COLOR

Transparent

YIELD

Curing only: 200 – 400 ft²/gal
(4.9 – 9.8 m²/L)

Second coat (dustproofing and
sealing): 400 – 600 ft²/gal
(9.8 – 14.7 m²/L)

Coverage varies with application
method, texture, and porosity of
surface.

STORAGE

Store in unopened containers in a
clean, dry area between 35 and 85° F
(2 and 29° C). Keep from freezing.

SHELF LIFE

18 months when properly stored.

VOC CONTENT

646 g/L, less water and exempt
solvents.

DESCRIPTION

MasterKure® CC 300 SB is a transparent, 30% solids, solvent-based, modified acrylic curing membrane. Apply it to damp or dry surfaces to provide a high-gloss finish. It complies with ASTM C 1315, Type I, Class A.

PRODUCT HIGHLIGHTS

- Solvent-based for excellent blush/whitening resistance
- Ensures high curing efficiency allowing concrete to attain its full strength potential
- Reduces surface absorption and dusting of concrete for easier cleaning and maintenance
- Retains moisture in concrete to minimize shrinkage cracking
- VOC compliant for EPA
- Compatible with most carpet and tile adhesives
- Higher solids to yield a high-gloss finish
- Good UV resistance for retention of transparency
- Low viscosity to provide easier application at cool temperatures
- Abrasion resistant to withstand foot traffic and provide extended wear
- Sprayable with suitable pump up canister sprayer
- Abrasion resistant for extended wear
- Reduced fluid penetration to increase stain resistance of concrete

APPLICATIONS

- Offices
- Warehouses
- Commercial buildings
- Interior or exterior

SUBSTRATES

- Concrete
- Decorative concrete

HOW TO APPLY

SURFACE PREPARATION

1. Freshly placed concrete must be properly finished. The surface is application ready when it is damp, but not wet, and when it cannot be marred by foot traffic.
2. Existing concrete surfaces should be thoroughly repaired and cleaned before application. Surface must be clean, dry and free of dust, oil, grease, sealers and all other surface contaminants that might inhibit proper bond of material.

APPLICATION

1. Stir MasterKure® CC 300 SB thoroughly before using.
2. Apply a continuous, uniform film by short-nap roller or lamb's wool applicator. Spraying is not recommended.
3. For curing, one coat may be sufficient. However, two coats may be required in hot and windy conditions. Apply evenly and uniformly as soon as possible after final finishing.
4. To seal and dustproof, two coats are required. Apply the second coat when all trades have completed their work and site is ready for occupancy.
5. Do not overapply or soak concrete surfaces with the curing compound. Do not allow the curing compound to pool on the surface. Over-application can result in alligatoring and mud cracking, whereby a film forms on the substrate before the material dries properly. Over-application may also cause opacity, as elements of the curing compound become trapped in the subsurface and cannot escape.

DRYING TIME

- Times are based on temperatures of 65 to 85° F (18 to 29° C) at 50% relative humidity.
- Light foot traffic or between coats: 4 hours
- Normal traffic: overnight
- Maximum hardness: 7 days
- Material will take longer to dry at either higher humidity or lower temperatures.

CLEAN UP

Clean tools and equipment with MasterSeal® 990 immediately after use and while MasterKure CC 300 SB is still wet.

FOR BEST PERFORMANCE

- MasterKure CC 300 SB may settle and must be stirred thoroughly before and during application.
- Do not thin.
- Keep away from heat and open flame.
- Application not recommended when surface temperatures exceed 120° F (49° C).
- For best appearance and performance, apply uniformly and at recommended coverage rates.
- If MasterKure CC 300 SB is to be applied in or near areas containing foodstuffs, they must be removed before application; do not return foodstuffs until MasterKure CC 300 SB has fully dried and all solvent vapors have dissipated.
- Heating Ventilation Air Conditioning (HVAC) units may draw solvent vapors into occupied building interiors. Solvent vapors can be irritating. Do not apply MasterKure CC 300 SB in or around buildings occupied by non-construction personnel without consulting building management and taking appropriate precautions. Use only with adequate ventilation and with a minimum of six air changes per hour.
- Do not apply to surfaces of joints to be caulked with sealants. Mask joints to avoid sealant-adhesion problems.

- Do not use on surfaces that are to receive concrete overlays or additional toppings or coatings.
- Not recommended as a release agent or where other sealers or treatments are to be later applied.
- Avoid excess moisture until material is fully cured.
- Although MasterKure CC 300 SB is compatible with a variety of tile, carpet and floor covering adhesives, a test application is always recommended.
- Can be applied to natural or colored concrete, but mottling or discoloration may occur.
- May highlight features and imperfections of the concrete surface.
- MasterKure CC 300 SB is considered a light-duty sealer; may rubber burn when subjected to forklift or other wheeled traffic.
- Mechanical methods are recommended for removing MasterKure CC 300 SB.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality

Technical Data

Composition

MasterKure® CC 300 SB is an acrylic polymer in a solvent carrier.

Compliances

- Recommended for concrete floors as defined in Table 1.1, ACI Standard 302.1R
- Federal Specification TT-C-800A
- AASHTO M-148
- ASTM C 1315, Type 1, Class B
- USDA compliant for use in meat and poultry areas when fully cured
- Corps of Engineers CRD-C-304, Type 1
- ASTM C 309, Type 1, Class A and B

Typical properties

PROPERTY	VALUE
Solids content, % by weight	30

Test Data

PROPERTY	RESULTS	TEST METHODS
Moisture Retention, kg/m² (applied at 200 ft ² /gal)		ASTM C 309
MasterKure CC 300 SB	0.21	
Test requirement	≤ 0.55	
Moisture Retention, kg/m² (applied at 300 ft ² /gal)		ASTM C 1315
MasterKure CC 300 SB	0.32	
Test requirement	≤ 0.4	

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting buildingsystems.basf.com, e-mailing your request to basfbcst@basf.com or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,
call ChemTrec® 1(800)424-9300.**

LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.