

# MasterSeal® P 179

Porous surface primer for MasterSeal NP 150™/NP 100™

FORMERLY SONOLASTIC® PRIMER 2000

## PACKAGING

One pint (473 ml) cans

## COLOR

Clear

## YIELD

35–40 ft<sup>2</sup>/pt (6.87–7.86 m<sup>2</sup>/L)

450 linear ft (137 m) for a ½"  
(13 mm) deep joint

## STORAGE

Store in unopened containers in a cool,  
dry area out of direct sunlight.

## SHELF LIFE

15 months when properly stored

## VOC CONTENT

738 g/L

less water and exempt solvents

## DESCRIPTION

MasterSeal P 179 is a quick-drying solvent-based primer for the Master Builders Solutions line of silyl-terminated-polyether sealants, MasterSeal NP 150/NP100 and NP 150/NP100 Tint Base.

## PRODUCT HIGHLIGHTS

- Solvent-based, quick-drying formula
- Promotes improved adhesion to porous substrates requiring a primer

4. Allow primer to dry tack-free before applying sealant. Dry time will vary depending on temperature and humidity.
5. Sealant must be applied the same day as primer.

## APPLICATIONS

- Exterior or interior
- Above grade
- Porous substrates such as concrete, masonry and stone

## DRYING TIME

Approximately 15 minutes at 70 °F (21 °C) and 50% humidity

## CLEANUP

Brushes and tools may be cleaned with MasterSeal 990.

## HOW TO APPLY

### SURFACE PREPARATION

1. Masonry and stone surfaces must be sound, clean, dry, and free of paint, grease, oil, dirt and foreign matter.
2. Concrete surfaces must be fully cured and free of laitance, moisture or form oils.
3. Where necessary, clean joint surfaces by grinding, sandblasting or mechanical abrading. Remove dust, dirt and loose particles before priming.

### APPLICATION

1. Apply MasterSeal P 179 to the cleaned joint surfaces by brushing on a thin, uniform coat. Make sure primer does not soak into substrate, but forms a continuous film.
2. Use primer as is; do not thin.
3. Too much primer may act as a bond breaker.

### FOR BEST PERFORMANCE

- MasterSeal NP 150/NP100 is typically a non-priming sealant. BASF always recommends a field test application prior to the start of a project. Allow the sealant to cure for 10–14 days prior to testing, depending on humidity.
- Do not use MasterSeal P 179 on nonporous surfaces. Consult Technical Service for recommendations.
- Make certain the most current versions of product data sheet and SDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.

## Technical Data

### Composition

MasterSeal P 179 is an organosilane dissolved in an organic solvent.

## Typical Properties

PROPERTY	VALUE
<b>Flash Point, °F (°C)</b>	65 (18)
<b>Dry time, min, at 70 °F (21 °C), 50% rh</b>	15
<b>Solids, by weight, %</b>	26

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.
- Do not prime backer rod.
- Do not prime metal or low porous substrates

### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.basf.us](http://www.master-builders-solutions.basf.us), e-mailing your request to [basfbcst@basf.com](mailto:basfbcst@basf.com) or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,  
call ChemTrec® 1(800)424-9300.**

### LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.