



We create chemistry

MasterEmaco[®] S 5410 CI

High-strength, rapid setting, shrinkage compensated, fibre reinforced, structural repair mortar with active corrosion inhibition

DESCRIPTION

MasterEmaco[®] S 5410 CI is a single component, extra high-strength, high modulus, shrinkage compensated structural repair mortar that meets the requirements of the new European Norm EN 1504 - 3 class R4. MasterEmaco S 5410 CI contains Portland cement, graded sands, selected polymer fibres and special additives to significantly reduce the risk and incidence of shrinkage cracking. When mixed with water, it forms a highly thixotropic mortar that can easily be spray or trowel applied.

RECOMMENDED USES

MasterEmaco[®] S 5410 CI is used for the structural repair of concrete elements such as:

- Columns, piers and cross beams of all bridges
- Cooling towers and chimneys and other industrial environments
- Tunnels, pipes, outfalls and all below ground construction especially in harsh ground conditions

FEATURES AND BENEFITS

- **Versatile** – Can be applied in extreme environments where active corrosion inhibition is required.
- **Shrinkage compensation systems and fibre reinforcement** – Minimize crack tendency.
- **Highly thixotropic** – Can be applied up to 50 mm without the need of secondary reinforcement.
- **High early and ultimate strengths** – Matches high strength concrete found in structures.
- **Outstanding workability** – Easy placing and finishing for applicators.
- **High modulus and excellent adhesion** – Ensuring load transfer in structural repair.
- **No primer required** – Allows rapid application at reduced cost.
- **Very low permeability to water and chlorides**
 - Protection of reinforcing steel.

TYPICAL PROPERTIES*

Typical properties when tested at 2.8l water/20kg powder

Appearance	Grey powder
Application thickness Overhead Max	10-50 mm /layer Not more than 30mm/layer
Density	Approx. 2.2 g/cm ³
Mixing water per 20kg bag	Approx. 2.4 – 2.8 litres
Working time	Approx 30 minutes
Application Temperature (support and material)	Between +5 and +35°C
Compressive strength EN 1260 - after 3 hours - after 1 day - after 7 days - after 28 days	≥15 MPa ≥15-30 MPa ≥ 40 MPa ≥ 60 MPa
E-Modulus (28 days) EN1504-3	≥ 20 GPa
Adhesion (28 days) EN 1504-3	≥ 2 MPa
Adhesion after Freeze/Thaw EN 1504-3	≥ 2 MPa
Adhesion after Thunder/Shower EN 1504-3	≥ 2 MPa
Adhesion after Adhesion after dry cycling EN 1504-3	≥ 2 MPa
Capillary absorption – E N 13 05 7	≤ 0.5 kg/m ² h ^{0.5}
Rapid chloride permeability ASTM C 1202:2012	Approx 300 coulombs (very low)

APPLICATION

Surface preparation - Concrete must be fully cured with a minimum direct tensile strength of 1.5 MPa. All loose traces of concrete or mortar, dust, grease oil, etc. must be removed. Damaged or contaminated concrete shall be removed to obtain a keyed aggregate exposed surface. Non-impact / vibrating cleaning methods, e.g. grit or high pressure water blasting are recommended. Cut the edges of the repair vertically to a minimum depth of 10 mm. Clean all exposed reinforcement to a bright steel condition and apply MasterEmaco 8100 AP zinc rich primer to exposed cleaned steel and allow to dry. Ensure concrete substrate is free of dust and pre-saturated for a minimum of 4 hours prior to commencing with the installation.



We create chemistry

MasterEmaco[®] S 5410 CI

Mixing - Only full bags are mixed. Damaged or opened bags should not be used. Mix **MasterEmaco[®] S 5410 CI** in a forced action pan mixer, or with a helical paddle attached to a low speed (300-600rpm) mixer for 3 minutes until a lump free, plastic consistency is achieved. Only use clean water. Mixing water needed: 2.4 to 2.8 litres per 20kg bag depending upon consistency required. Allow the mortar to rest for 2 - 3 minutes and then remix briefly, adjusting the consistency when required, without exceeding the maximum water demand.

Priming Concrete - No special primer is required. Thoroughly saturate the surface of the concrete to provide a saturated surface dry condition. Poor quality concrete may require soaking for a significant length of time. Any surface water should be removed using an oil free compressed airiest.

Mortar application - The minimum temperatures must be maintained during application and for at least 24 hours thereafter for optimum curing of the product. The prepared substrate should be pre-soaked, preferably for 24 hours, but at least 2 hours before applying **MasterEmaco[®] S 5410 CI**. The surface must be saturated surface dry, but without standing water. **MasterEmaco[®] S 5410 CI** can be spray or hand applied. Apply mixed product directly to the prepared damp substrate. Spraying the material with the necessary pressure will ensure good adhesion of the material. A thin scraper coat or contact layer before building up to the required thickness, wet on wet, will improve adhesion especially in case of hand application. Apply to the desired layer thickness of 10 to max 50 mm and level using a screeding bar, trowel or wooden board. Can be applied in thicker layers in smaller patches or where additional reinforcement is present. Smoothing with a trowel or finishing by float or sponge can be done as soon as the mortar has begun to stiffen.

CURING

The following curing methods are advised: Polyethylene film, damp cloths, **MasterKure[®]** curing agents.

ESTIMATING DATA

One 20kg bag will yield approximately 10 litres of mortar. Approx. 2.2 kg of mixed product per m² per mm layer thickness. This consumption is theoretical and depends on the roughness of the support amount of rebar, wastage etc, for which reason it should be verified in each particular job by means of "in situ" tests.

PACKAGING

MasterEmaco[®] S 5410 CI is available in 20kg bags.

SHELF-LIFE

Store in cool and dry warehouse conditions. Shelf life in these conditions is 12 months from date of manufacture in unopened original bags.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office.



We create chemistry

MasterEmaco[®] S 5410 CI

NOTE

Technical support, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative. BASF shall not be liable for technical advice provided.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods. Undertaking such tests is not, and shall not be deemed to be, an admission of liability or an assumption of any risk, loss, damage or liability.

QUALITY AND RESPONSIBLE CARE

All products originating from BASF Construction Chemicals South Africa are Manufactured under a management system independently certified to conform to the requirements of the quality (ISO 9001), environmental and occupational health & safety standards.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals South Africa (Pty) Ltd

852 Sixteenth Road, Midrand

PO Box 2803, Halfway House, 1685

Tel: +27 11 203 2405

Fax: +27 11 2032679

www.master-builders-solutions.basf.co.za

Revision Date: 02/06/2017