

MasterSeal[®] P 700

Fast drying solvent base bitumen primer for bitumen sheet membrane

DESCRIPTION

MasterSeal P 700 is a blend of high penetration grade bitumen with less boiling range hydrocarbon solvents. It is generally used as an all-purpose bituminous primer on steel and concrete, prior to the application of waterproofing membranes.

PRIMARY USES

MasterSeal P 700 is suitable for sealing of concrete surfaces, as well as for filling of fissures and joints. To improve adhesion of bitumen waterproofing membranes in below grade and roof deck applications.

PACKAGING

MasterSeal P 700 is supplied in 20 litre containers.

COLOUR

Black

TECHNICAL DATA*

Viscosity @ 25°C (ford cup # 4)	35-70 seconds
Distillation - by volume % Upto 225°C Upto 360°C	35 min. 65 max.
Test on residue from distillation Penetration @ 25°C Solubility in trichloroethylene	25-35 dmm 99.0% min.
<i>The above is produced to comply with the specification requirement of ASTM D41-85</i>	
Solids Content	55 ± 3%
Specific Gravity	Approx. 0.85-0.9
Drying time	2 ± 1 hours
Flashpoint	35°C

COVERAGE

Surfaces are to be free from rust and dust. The primer can be applied with a brush, roller or airless spray gun. The application will differ based on the surface. On steel surfaces application rates more than 10m² per liter. On porous concrete this may be as low as 3m² per liter.

In accordance with specification requirements otherwise, an application rate of 1 litre/m² will result in a DFT of 0.55mm.

HEALTH & SAFETY

MasterSeal P 700 contains a large proportion of flammable solvent and must not be exposed to a naked flame or sparks.

The flash point (COC) is 35°C. The vapor given off is narcotic and care should be taken not to inhale it. If applying in an enclosed area, provide adequate ventilation and wear breathing apparatus.

Do not allow smoking at the time of application.

STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.



We create chemistry

MasterSeal[®] P 700

SHELF LIFE

Shelf life is 12 months from date of manufacture when stored in undamaged, unopened packaging.

QUALITY AND RESPONSIBLE CARE

All products originating from BASF Construction Chemicals South Africa are manufactured under a management system independently certified to conform to the requirements of the quality (ISO 9001), environmental and occupational health & safety standards.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals South Africa (Pty) Ltd

852 Sixteenth Road, Midrand

PO Box 2803, Halfway House, 1685

Tel: +27 11 203 2405

Fax: +27 11 203 2679

www.master-builders-solutions.basf.co.za

Revision Date: 01/09/2017

Please refer to the BASF website to ensure that you have the latest version of this Technical Data Sheet.

MASTER[®]
» BUILDERS
SOLUTIONS