

Overview Chemical Resistance of MasterTop BC 308

Chemicals	MasterTop BC 308
Acetone	(+)
Acetic acid up to 5 %	(+)
Ammonia up to 32 %	+, matt
Brake fluid	+
Butanol	+
Calcium hydroxide saturated	+
Caustic soda solution up to 10 %	+
Caustic soda solution up to 50 %	+
Chromic acid up to 20 %	+, discoloration
Citric acid 10 %	+
Diesel fuel	+
Engine oil	+
Ethanol	(+)
Ethyl acetate	(+)
Ferric chloride solution	+
Formaldehyde up to 38 %	+
Formic acid up to 2 %	(+)
Formic acid up to 5 %	-
Fruit juice	+
Heating oil	+
Hydraulic fluid	+
Hydrochloric acid up to 20 %	+, discoloration
Hydrofluoric acid up to 20 %	-
Hydrogen peroxide up to 30 %	(+), matt
Jet fuel	+
Kerosene	+
Lactic acid up to 10 %	+
Magnesium chloride solution up to 35 %	+
Methanol	(+)
Methylene chloride	-
Methyl ethyl ketone (MEK)	-
Nitric acid up to 10 %	(+)
Nitric acid up to 20 %	-
Oxalic acid up to 10 %	+

Chemicals	MasterTop BC 308
Phenol up to 2 %	+
Phosphoric acid 20 %	(+), discoloration, matt
Potassium hydroxide solution up to 50 %	+
Propanol	+
Skydrol	(+)
Sodium carbonate, saturated	+
Sodium chloride solution, any	+
Sodium sulphate solution, any	+
Sugar	+
Sulphuric acid up to 40 %	+, discoloration, matt
Sulphuric acid up to 90 %	-
Transmission fluid	+
Turpentine	+
Vegetable oils	+
Water	+
Xylene	+

+ resistant for 3 months
 (+) resistant for 3 days
 - not resistant

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with BASF and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.