

MasterFinish RL 218

Form release agent for fair-faced concrete, free from cavities and pores

DESCRIPTION OF PRODUCT

MasterFinish RL 218 is a chemical-physical form release agent based on highly refined mineral oils, biodegradable additives and dearomatized solvents. MasterFinish RL 218 has been specially formulated to provide an easy and complete release of the concrete from forms and a significantly improved quality of the concrete surface which is free from cavities and pores.

FEATURES AND BENEFITS

It gives an improved exposed surface of concrete economically by reducing the application time, quicker stripping, easier. Keeps the formwork well clean, reduces the usual expenditure on cleaning considerably and has an anti-corrosive effect, thus increasing the life of the formwork. Its low viscosity ensures easy and economical application.

If the product is applied in thin layers the adhesion of subsequent coatings (e.g. plasters, paints) is not impaired. Foams like polystyrene and similar will not be attacked.

- Excellent corrosion inhibition for steel forms
- Ready-to-use
- For all types of concrete
- For normal or delayed stripping

FIELDS OF APPLICATION

MasterFinish RL 218 is suitable for all non-absorbing types of formwork. It may be applied on heated horizontal and vertical formwork up to 80 °C.

COVERAGE

The coverage of MasterFinish RL 218 depends upon the application method. If applied uniformly by a sprayer at a constant pressure of 5 bars on metallic or on impervious material the coverage rate is 85 -125 m²/litre.

PROCEDURA DE UTILIZARE

MasterFinish RL 218 is a ready-to-use product that can be applied either by a sprayer, brush or a roller on any type of forms.

The spray application should be carefully carried out in order to achieve a satisfactory and even coverage.

The spraying should be done at a suitable distance from the mould (approx. 100 cm) so that the release agent is evenly distributed in a uniform film thickness.

During spraying, it is critical that the spraying pressure is adequately high (4-5 bars) and that the gun, especially the nozzle is completely tight in order to avoid dripping.

When spraying with a portable handgun, a slit nozzle with a spraying angle from 65 to 80° has been found to give the best results.

HANDLING

Avoid contact with skin and eyes and inhalation of vapors. It will be taken into consideration and will respect with labor protection measures foreseen when handling chemicals.

FIRST AID MEASURES

After skin contact: Wash immediately with soap and water and rinse extensively. After eye contact: rinse eyes thoroughly for 15 min. under running water, holding the eyelids apart and seek ophthalmology.

ENVIRONMENTAL MEASURES

Do not discharge product on soil, groundwater, surface water course or sewage system, even in small quantities. Observe the national regulations regarding environmental protection.

SAFETY INSTRUCTIONS

For details please ask for updated safety data sheet at tel.: 0344 520 100/102 or by e-mail: constructii-romania@basf.com

CONSULTANCY

For specific advice or consulting, please contact technical representative in your area, or contact us directly at tel.: 0344 520 100/102.

MasterFinish RL 218

Form release agent for fair-faced concrete, free from cavities and pores

Products Parameters	
Chemical composition:	Refined mineral oils, dearomatized solvents
Appearance:	Yellowish transparent liquid
Form temperature	-10°C ÷ 80°C
Specific gravity @ 20°C:	0,79 ± 0,02 g/cm ³
Viscosity @ 20°C	Approx. 3 cSt.
Logistics	
Valabilitate	12 months if stored according to manufacturer's instructions in unopened container.
Storage conditions	Store in original sealed containers and at temperatures between 5°C and 40°C. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.
Dangerous goods ADR / SDR	3/3925/III

Legal notice

All technical information and recommendations contained herein are based on our current knowledge and experience. This document serves to describe the composition of the product, characteristics and its ability to process and commissioning work, respecting the instructions on transportation, storage and processing. The manufacturer does not assume any responsibility if conditions are not met. Due to the many factors that can affect the final results cannot guarantee certain properties of the product or its suitability for a specific use.

The buyer has the obligation to test the suitability of the product before proceeding to complete its application.

Product performance must be verified by tests performed by specialized personnel and adapted to the local conditions, external influences, etc.

Any descriptions, drawing, photographs, data, proportions, weight, etc. mentioned in this document may change without notice.

It is responsibility of our product to ensure that property rights are respected all laws existing regulations

Users should check the latest version of Data Sheet for the product, copies of which will be supplied on request.

Date: 01/08/2016