

# MasterSeal® P 770

## Two-component primer based on Xolutec - Technology for MasterSeal Systems

### DESCRIPTION

**MasterSeal P 770** is a two component primer based on Xolutec - Technology, providing high substrate penetration and acting as bond promoter for the subsequent **MasterSeal** systems, e.g. **MasterSeal 7000 CR**.

### Xolutec™ a new dimension in durability

**Xolutec** is an innovative and smart way of combining complementary chemistries. When the material is mixed on site a cross linked interpenetrating network (IPN) is formed enhancing the overall material properties. By controlling the cross-linking density, the properties of Xolutec can be adjusted depending on the product performance required, e.g. this allows the formulation of materials with varying degrees of toughness and flexibility. Xolutec is very low in volatile organic components (VOC), is quick and easy to apply with both spray and hand application depending on requirements. It cures rapidly even at low temperature, reducing application time thus enabling fast return to service and minimizing downtime.

This technology tolerates a wide variety of different site conditions, greatly expanding the application window and reducing the potential for delays and failures. Long maintenance cycles and lower life cycle costs significantly reduce total cost of ownership.

### FIELDS OF APPLICATION

**MasterSeal P 770** is used as primer on mineral substrates for **MasterSeal** systems. The primer coat will improve the adhesion and prevent the appearance of pinholes or bubbles in the subsequent hardened coating.

### FEATURES AND BENEFITS

- Low viscosity
- Easy to apply
- Excellent penetration
- Seals pores and capillaries
- Moisture tolerant - can be applied on substrates with high residual humidity

- Excellent bond to substrate
- Does not contain solvents.

### APPROVALS AND CERTIFICATES

CE Certification as primer for **MasterSeal M 790** in the system **MasterSeal 7000 CR** according to EN 1504-2.

### PACKAGING

**MasterSeal P 770** is available in 5kg kits consisting of 2.2kg Part A and 2.8kg Part B

### COLOUR

Milky-ivory

### APPLICATION METHOD

#### Surface preparation:

All substrates (new and old) must be structurally sound, dry, free of laitance and loose particles and clean of oil, grease, rubber skid marks, paint stains and other adhesion impairing contaminants.

**Concrete:** The surface should be prepared by shot blasting, high-pressure water jetting or other suitable mechanical method. After preparation, concrete and other cementitious substrates must have a minimum pull off strength of 1 N/mm<sup>2</sup>. Very rough / irregular substrates on walls should be levelled before application with a suitable fairing coat, e.g. **MasterEmaco N 907**. On floors a suitable repair or levelling solution should be used.

Wall/Floor connections must be rounded by using suitable products e.g. **MasterSeal 590**.

The substrate should be visibly dry. Substrate temperature must be minimum +5°C and maximum +40°C. The temperature of the contact surfaces must be at least 3°C above the ambient dew point temperature.

#### Mixing

**MasterSeal P 770** is supplied in working kits which are pre-packaged in the exact mixing ratio.

# MasterSeal® P 770

Pour the entire content of Part A into the container of Part B and mix with a mechanical drill and paddle at low speed (max. 400 rpm) for at least 3 minutes. Scrape the sides and the bottom of the container several times to ensure complete mixing. Keep the mixer blades submerged in the coating to avoid introducing air bubbles.

**Do not mix part kits and do not mix by hand!**

## Hand Application

After mixing, **MasterSeal P 770** is applied to the prepared substrate by brush or roller. The curing time of the material is influenced by the ambient, material and substrate temperatures.

At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the pot life, open time and curing times are shortened accordingly. To fully cure, the material, substrate and application temperature should not fall below the minimum. The temperature of the contact surfaces must be at least 3°C above the ambient dew point temperature.

**MasterSeal P 770** dries as an intense transparent film (within 5 hours @ 20°C). In case there are holes not covered by primer, please apply a second coat of primer. Wait for at least 5 hours (@ 20°C) before applying **MasterSeal** systems.

## COVERAGE

The consumption of **MasterSeal P 770** is approximately 0.25-0.4kg/m<sup>2</sup>.

This consumption is theoretical and can vary according to the absorption and roughness of the substrate. It is essential to carry out representative trials on site to evaluate the exact consumption

## WORKING TIME

Approximately 20 minutes at 20°C ambient and substrate temperature.

## FINISHING & CLEANING

Tools can be cleaned with **MasterTop THN 2** while still wet. Once cured, the material can only be removed mechanically.

## STORAGE & SHELF LIFE

**MasterSeal P 770** should be stored in original containers under dry conditions at temperatures between 10-25°C preferably. Protect from frost and no permanent storage over +30°C. Shelf life under these conditions is 12 months for both parts.

## WATCHPOINTS

- For maximum application performance do not apply at temperatures below +5°C nor above +40°C. For higher temperatures consult BASF Technical Services department.
- Eventual separation of Part A can occur – this is no product failure and the material can be easily re-homogenized by mixing.
- Do not add any solvents or other components to **MasterSeal P 770** mixes.

## HANDLING / TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed. Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

# MasterSeal<sup>®</sup> P 770


## TECHNICAL DATA\*

Technical data			
Property	Standard	Unit	Data
Density of mixed material	EN ISO 2811-1	g/cm <sup>3</sup>	approx. 1.2
Viscosity of mixed material	EN ISO 3219	mPas	approx. 650
Application temperature (substrate)	-	°C	from +5 to +40
Pot-life at +5°C at +10°C at +20°C at +30°C		minutes	approx. 30 approx. 25 approx. 20 approx. 10
Dry to touch at +20°C		hours	approx. 5
Ready for pedestrian traffic / Re-coating interval at +10°C at +20°C at +30°C		hours	min. 11 min. 5 min. 2
Fully cured at +10°C at +20°C at +30°C		days	7 5 2
Glass transition temperature after 28 days	EN 12614	°C	55
Adhesion to concrete after 28 days	EN 1542	N/mm <sup>2</sup>	> 2.0
Adhesion in combination with subsequent layers of - <b>MasterSeal M 790</b> (Xolutec)	EN 1542	N/mm <sup>2</sup>	> 2.5

**Note:** Data are measured at 21°C ± 2°C and 60% ± 10% relative humidity if not stated differently. Higher temperatures and/or higher relative humidity can shorten hardening/curing times, and vice versa. Technical data shown are statistical results and do not correspond to guaranteed minima. Tolerances are those described in appropriate performance.

# MasterSeal<sup>®</sup> P 770

**CE-marking (EN 1504-2)**

 0921,0370	
<b>BASF Coatings GmbH</b> <b>Glasuritstraße 1</b> <b>D-48165 Münster</b>  16 DE0269/02	
<b>MasterSeal M 790 (DE0269/02)</b> <b>EN 1504-2:2004</b>	
Surface protection product/coating (Primer: MasterSeal P 770) EN 1504-2 Principles 1.3/2.2/5.1/6.1/8.2	
Reaction to fire	Class E
Abrasion resistance	Loss of mass < 3000 mg
Permeability to CO <sub>2</sub>	s <sub>D</sub> > 50 m
Water vapour permeability	Class III
Capillary absorption and permeability to water	w < 0,1 kg/m <sup>2</sup> h <sup>0,5</sup>
Thermal compatibility	≥ 1,5 N/mm <sup>2</sup> Pass
Resistance to severe chemical attack	Reduction in hardness < 50 %
Class I: 4a,6a,9,9a,13,15	
Class III: 1,2,3,4,5,5a,6,7,10,11,12,14,15a	
Crack bridging ability	A3 (23 °C) A2 (-10 °C) B3.1 (23 °C) B2 (-10 °C)
Impact resistance	Class III
Adhesion strength by pull off test	≥ 1,5 N/mm <sup>2</sup>
Artificial weathering	Pass
Dangerous substances	Comply with 5.3 (EN 1504-2)

® = Registered trademark of the BASF-Group in many countries.

\* Properties listed are based on laboratory controlled tests.

**BASF\_CC-UAE/SI\_P770\_11\_17/v1/**

**STATEMENT OF RESPONSIBILITY**

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

**NOTE**

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.