

MasterLife® WP 3760

(Formerly known as Masterseal 501 WA)

Crystalline waterproofing admixture for concrete & mortars

DESCRIPTION

MasterLife WP 3760 crystalline waterproofing powder admixture is an integral crystalline capillary waterproofing admixture for concrete. It is designed for use in above- and below-grade applications.

MasterLife WP 3760 consists of Portland cement, very fine treated silica sand and various active, proprietary chemicals. These active chemicals react with the moisture in fresh concrete with the by-products of cement hydration to cause a reaction, which generates an insoluble crystalline deposit throughout the pores and capillary tracts of the concrete. Thus the concrete with **MasterLife WP 3760** reduces water permeability. This product also has a self-healing property under presence of moisture and can heal cracks below 0.4 mm.

APPLICATIONS

MasterLife WP 3760 should be used in all structural concrete that is constantly or intermittently in contact with water such as sea walls, tunnels, basements, structural and pre-cast concrete. **MasterLife WP 3760** can also be used as crystalline waterproofing admixture for cement mortars and plasters. To waterproof structures such as:

- Building Basement and foundations
- Sewage and water treatment plants
- Dams, canals, Tunnels, Harbours
- Tunnel and subway systems
- Water reservoirs
- Concrete pipes
- Parking structures
- Pre-Cast, Cast-in-Place and Shotcrete applications
- Swimming pools
- Retaining walls & sea defense walls

FEATURES

- Crystalline cementitious material
- Integral addition
- Reduces concrete permeability

- Allows concrete to breathe
- Non toxic
- Becomes an integral part of the concrete

BENEFITS

- Reduces penetration of water and other liquids
- Can seal hairline cracks up to 0.4 mm.
- Resists positive and negative side hydrostatic pressure
- Protects against sewage and industrial wastes
- Less expensive than traditional methods
- Added to the concrete at time of batching and therefore is not subject to climatic restraints

PACKAGING

MasterLife WP 3760 is available in 5kg & 25kg pack.

PERFORMANCE CHARACTERISTICS

Setting Time:

MasterLife WP 3760 admixture has little to no effect on concrete setting time within the recommended dosage range. However, it is recommended to test this in case any additives or blended cementitious combinations are used in concrete.

Permeability:

MasterLife WP 3760 capillary waterproofing admixture is a portland cement-based crystalline cementitious material that reacts in concrete to form insoluble crystalline hydration products in the capillary pores/capillary tracts of the concrete. These crystalline hydration products are deposited and fill the pores and hairline cracks, effectively reduce the permeability of concrete, its capillary absorption and penetration of water and other liquids into the concrete.

MasterLife® WP 3760

(Formerly known as Masterseal 501 WA)

Typical Data for MasterLife WP 3760 admixture @ 1% by mass of cement.

OPC	Fly Ash	w/b	water	20mm	10mm	sand	MasterGlenium	MasterLife WP 3760
370	120	0.34	166.5	530	530	708	0.6%	1%

Specification	Test Results
Water Permeability coefficient - 5×10^{-13} m/s (DIN1048 Part 5)	1.3×10^{-13}
Water Penetration depth – Below 15mm (DIN1048 Part 5)	6.67mm
Concrete water proofing admixture shall of the crystalline growth type	SEM Report shows Crystalline growth and lower void in concrete relative to untreated concrete mixture.
Water Penetration	Reduction up to 30 to 35% relative to untreated concrete mixture
Workability	MasterLife WP 3760 has little or no effect on workability
Setting time of concrete	relative to untreated concrete mixture

PERFORMANCE TEST DATA

Aspect	Free Flowing grey powder
Bulk density	1.350 ± 0.02 gm/cm ³
Chloride content	“chloride free” to EN 934

DOSAGE

As a guide, a dosage of 1000 grams per 100kg of cementitious content is recommended. Dosage up to 2000 grams per 100kg of cementitious content can be used in special requirements. For addition to ready mix concrete, a typical dosage of 5kg per cubic meter of concrete is best recommended.

For addition information on **MasterLife WP 3760** or on its use in developing concrete mixes with special performance characteristics, contact your local BASF representative.

Points to remember when producing waterproof concrete:

- Ensure water / cement ratio is less than 0.5
- Addition of good superplasticiser from the **MasterRheobuild** or **MasterGlenium** range is advised to achieve minimum water/cement ratio.
- Place concrete quickly and compact it well.
- Ensure complete curing with a **MasterKure** curing compound.

DISPENSING & MIXING

MasterLife WP 3760 admixture is batched at the concrete production plant in a manner similar to that for cement or other cementitious materials. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer. Provide at least 5 minutes of mixing after the addition of **MasterLife WP 3760** admixture to ensure thorough and uniform distribution of the admixture in the concrete mixture.

MasterLife[®] WP 3760

(Formerly known as Masterseal 501 WA)

COMPATIBILITY

MasterLife WP 3760 admixture can be used with portland cements approved under ASTM and EN specifications. It is compatible with most concrete admixtures, including all BASF admixtures. **MasterLife WP 3760** admixture is recommended for use with high-range water-reducing admixtures, such as the **MasterGlenium** series, for maximum workability while maintaining a low water-to-cementitious materials ratio.

MasterLife WP 3760 is also compatible with slag and pozzolans such as fly ash, GGBS and silica fume.

CORROSIVITY – NON CHLORIDE , NON CORROSIVE

MasterLife WP 3760 will neither initiate nor promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanized steel floor and roof systems. Neither calcium chloride nor any calcium chloride-based ingredients are used in the manufacture of **MasterLife WP 3760**. In all concrete application, **MasterLife WP 3760** will conform to the most stringent or minimum chloride ion limits currently suggested by construction industry standards and practices.

WORKABILITY

MasterLife WP 3760 has little or no effect on workability of concrete. Prior site trials are advised to assess the effect, and any increase or decrease in the workability can be adjusted by adjusting the admixture dosage or amount of water in use.

It is strongly recommended that concrete should be properly cured particularly in hot, windy and dry climates.

STORAGE / SHELF LIFE

MasterLife WP 3760 must be stored where temperatures do not drop below +5°C.

Shelf life is 6 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult your local BASF representative.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Life_WP3760_11_15/v1/

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.